



COATING SYSTEM

Roofing Granules: All roofing granules must be Title 24 compliant. To be used in high foot traffic areas.

For granulated walkways, measure and mask the edges of the walkway (X) 2' to 4' wide (.61m to 1.22m) depending on use. Apply top coat at a rate of 1 gallon per square for 16 wet mils (3.79 liter/9.29 m², 406.4 microns). Broadcast granules into the top coat at a rate between 30 to 50 lbs per 100 square feet (13.6 to 22.7 kg per 9.29m²) or until rejection. After broadcasting granules immediately remove masking tape. Allow top coat to cure with granules. Remove any excess granule by sweeping or vacuuming. Inspect for any inefficiencies. Consider using an off-setting color for top coat walkway, e.g., Tan, Grey, Yellow.

GRANULATED WALKWAY



Phone: 702-966-9961 | www.EverRoof.com